

TECHNICAL DATA ARTICLE CIERVO

Bovine leather half grain

Chrome tanned

Colour fastness to light: 5 DIN 50004

Colour fastness to/for rubbing Dry 1000 C. / Wet 250 C. DIN 53339

Tear Strength, single edge tear Above 20 N DIN 53329

Flexing endurance: Minimum 100.000 C DIN 53351

Finish Adhesion: Minimum 1,5 N / 10 mm IUF 470

Determination of pH: Above 3,5 N DIN 53312

Thickness: 1,3 mm to 1.5 mm

Free of pentachlorophenol, chemical substance detrimental for the ozone layer.

The leather chrome tanned, re-tanned with synthetic resin to give body and elasticity at the same time. The dye is done with aniline in big drum.

The refinition is made with polyurethane in water.

Cleaning of the leather must be made with water and neutral soap, or products supplied by manufacturers of leather.