


001 - ANGORA DIS.2



028



026

MARIANO FARRUGIA T E S S U T I

ANGORA DIS. 2



CARACTERÍSTICAS TÉCNICAS / TECHNICAL DETAILS

Composición / Composition		100% VW (lana virgen)
Ancho / Width		150 cm. ±2%
Peso / Weight		550 gr/m ² ±5%
Espesor / Thickness		1,30 mm ±0,1

Solidez del color a la luz Colour fastness to light	XENO ISO 105 B12	4/5
Solidez del color al frote Colour fastness to rubbing	CROCK METER ISO 105 X12	4/5 SECO - DRY 4 HÚMEDO - WET

Resistencia al pilling Pilling resistance	ISO 12945-2	3/4
--	-------------	-----

Resistencia a la abrasión Abrasion resistance	MARTINDALE ISO 12947-2	65.000 CICLOS / RUBS
--	---------------------------	----------------------

Tratamiento especial anti-pilling
Special anti-pilling treatment

Este tejido ha sido tratado en su acabado con el sistema termofísico KD y es inalterable. Ni el lavado ni el planchado podrán modificar las características de la tela.
This fabric has been treated in finishing with the Termophysical System "KD" and it is inalterable. Neither wetting nor ironing modify the characteristic of the cloth.

Símbolos de cuidado y limpieza / Care label


Se aconseja lavado en seco
Dry clean suggest

Comportamiento frente al fuego / Fire retardant	ITALIA / ITALY	UNI 9175 Class 1IM
	EUROPA / EUROPE	EN 1021-1:2006 EN 1021-2:2006
	INGLATERRA / ENGLAND	BS 5852 IS 0 (cigarette) BS 5852 IS 1 (match)
	EE.UU. / U.S.A.	California TB 117:2013
	NAUTICA / NAUTICAL	FTP Code 307(88): 10 Annex 1 Part 8 ex. IMO res. A 652 (16)

Sólo bajo pedido (min 200 mtl en 4 semanas) Only on request (min 200 mtl in 4 weeks)	FRANCIA / FRANCE	NF-P 503 Class M1
	INGLATERRA / ENGLAND	BS 5852 IS CRIB 5
	ALEMANIA / GERMANY	DIN 4102-1 Class B1

Estos valores se dan únicamente para información de buena fe y no pueden considerarse en ningún caso vinculantes. No se responde del uso inapropiado. **Se permiten ligeras diferencias de color entre diferentes lotes.** The overmentioned data correspond to average values communicated in good faith, but they cannot be considered as a contract document. The company is not responsible for any inappropriate use of the product. **Slight colour differences among several lots are admitted.**

www.mfarrugia.com

info@mfarrugia.com

+34 968 75 10 39 FAX +34 968 79 26 72

Polígono Industrial La Herrada C/ Príncipe de Asturias 41 Apartado 452 30510 Yecla Murcia Spain


A N G O R A D I S . 2

MARIANO FARRUGIA

T E S S U T I



010 - ANGORA DIS.2



026



027

A N G O R A D I S . 2



002 - ANGORA DIS.2



001



003



002



003 - ANGORA DIS.2




004 - ANGORA DIS.2



011



012



025



007



005 - ANGORA DIS.2



006 - ANGORA DIS.2




013



014




017




016




007 - ANGORA DIS.2



008 - ANGORA DIS.2




023




020



010



008



009 - ANGORA DIS.2