

# MARIANO FARRUGIA

## T E S S U T I



### IDRIS COMBI

#### CARACTERÍSTICAS TÉCNICAS / TECHNICAL DETAILS

Composición / <i>Composition</i>	<b>100% PP FR (nativa)</b>	
Ancho / <i>Width</i>	<b>140 cm. ±2%</b>	
Peso / <i>Weight</i>	<b>350 gr/m<sup>2</sup> ±5%</b>	
Solidez del color a la luz artificial <i>Colour fastness to artificial light</i>	XENO ISO 105 B02	<b>4-5</b>
Solidez del color al frote <i>Colour fastness to rubbing</i>	CROCK METER ISO 105 X12	<b>5 SECO - DRY</b> <b>4/5 HÚMEDO - WET</b>
Resistencia al pilling <i>Pilling resistance</i>	ISO 12945-2	<b>4/5</b>
Resistencia al deslizamiento de la costura <i>Seam slippage</i>	EN ISO 13936-2	<b>1,50 mm.</b>
Resistencia a la abrasión <i>Abrasion resistance</i>	MARTINDALE ISO 12947-2	<b>≥ 50.000 CICLOS / RUBS</b>
Resistente a <i>Resistant to</i>	Este hilo es: Repelente al agua - antiestático - hipoalergénico - antibacteriano - no encoge <i>This yarn is: Water repellent - antistatic - hypoallergenic - antibacterial - no-shrink</i>	
Símbolos de cuidado y limpieza / <i>Care label</i>	<p>Se aconseja lavado en seco <i>Dry clean suggest</i></p>	
ATENCIÓN <i>WARNING</i>	<i>Artículo no válido para exterior</i> <i>Not suitable for external/outdoor use</i>	
Comportamiento frente al fuego / <i>Fire retardant</i>	ITALIA / <i>ITALY</i> EUROPA / <i>EUROPE</i>  INGLATERRA / <i>ENGLAND</i> FRANCIA / <i>FRANCE</i>  EE.UU. / <i>U.S.A.</i> NAUTICA / <i>NAUTICAL</i>	UNI 9175 Class 11M EN 1021:2006-1 EN 1021:2006-2  BS 5852 IS 11 (CRIB 5) NF D 60-013:2006 (art. AM 18) California TB 117:2013 FTP Code 307(88): 10 Annex 1 Part 8

Estos valores se dan únicamente para información de buena fe y no pueden considerarse en ningún caso vinculantes. No se responde del uso inapropiado. **Se permiten ligeras diferencias de color entre diferentes lotes.** *The overmentioned data correspond to average values communicated in good faith, but they cannot be considered as a contract document. The company is not responsible for any inappropriate use of the product. Slight colour differences among several lots are admitted.*

[www.mfarrugia.com](http://www.mfarrugia.com)

[info@mfarrugia.com](mailto:info@mfarrugia.com)

+34 968 75 10 39 FAX +34 968 79 26 72