

MARIANO FARRUGIA  
T E S S U T I


**KENIA CLUB**



**CARACTERÍSTICAS TÉCNICAS / TECHNICAL DETAILS**

Composición / <i>Composition</i>		<b>84% PVC - 16% CO</b>
Ancho / <i>Width</i>		<b>137 cm.</b>
Peso / <i>Weight</i>		<b>700 ±5% gr/m<sup>2</sup></b>
Espesor / <i>Thickness</i>		<b>1,2 mm ±0,2 mm</b>
Resistencia a la tracción <i>Tensile resistance</i>	EN ISO 1421	<b>&gt; 24 daN/5cm LARGO - LENGTH</b> <b>&gt; 15 daN/5cm ANCHO-WIDTH</b>
Resistencia a la rotura <i>Extension at break</i>	ISO 4674 - 1B	<b>&gt; 13% LARGO - LENGTH</b> <b>&gt; 10% ANCHO - WIDTH</b>
Solidez del color al frote <i>Colour fastness to rubbing</i>	ISO 105 X 12	<b>4/5 SECO - DRY</b> <b>4/5 HÚMEDO - WET</b>
Variación cromática de la superficie <i>Colour change of surface</i>	ISO 105 X 12	<b>4/5 SECO - DRY</b> <b>4/5 HÚMEDO - WET</b>
Solidez del color a la luz artificial <i>Colour fastness to artificial light</i>	XENO ISO 105 B 02	<b>&gt; 5</b>
Resistencia a la abrasión <i>Abrasion resistance</i>	MARTINDALE EN ISO 5470-2	<b>&gt; 70.000 CICLOS - RUBS</b>
Cumple con <i>Passes</i>	<b>REACH standard</b>	

**Símbolos de cuidado y limpieza / Care label**



Comportamiento frente al fuego / <i>Fire retardant</i>	ITALIA / <i>ITALY</i>	UNI 9175 Class 1IM
	EUROPA / <i>EUROPE</i>	EN 1021:2014 part 1 EN 1021:2014 part 2
	INGLATERRA / <i>ENGLAND</i>	BS 5852 IS 0 (cigarette) BS 5852 IS 1 (match)
	ALEMANIA / <i>GERMANY</i>	DIN 4102-1 Class B1
	FRANCIA / <i>FRANCE</i>	NF-P 503 Class M1
	EE.UU. / <i>U.S.A.</i>	California TB 117:2013
	NAUTICA / <i>NAUTICAL</i>	FTP Code 307(88); 10 Annex 1 Part 8

Algunos tintes utilizados en la ropa (ej. vaqueros) pueden migrar en colores claros de este artículo. Este fenómeno aumenta con la humedad y temperatura. No se asume ninguna responsabilidad por la transferencia de color. *Some dyes for clothing and accessories (ex. jeans) may migrate to the bright colour of this article. This phenomenon increases with the humidity and the temperature. No responsibility is assumed for the colour transfer.*

Estos valores se dan únicamente para información de buena fe y no pueden considerarse en ningún caso vinculantes. No se responde del uso inapropiado. **Se permiten ligeras diferencias de color entre diferentes lotes.** *The overmentioned data correspond to average values communicated in good faith, but they cannot be considered as a contract document. The company is not responsible for any inappropriate use of the product. Slight colour differences among several lots are admitted.*

[www.mfarrugia.com](http://www.mfarrugia.com)

[info@mfarrugia.com](mailto:info@mfarrugia.com)

+34 968 75 10 39 FAX +34 968 79 26 72

MARIANO FARRUGIA

T E S S U T I

K E N I A C L U B




K E N I A C L U B



001




002



003


K E N I A C L U B




004



005



006



007



008