

MARIANO FARRUGIA

T E S S U T I



KALAHARI

CARACTERÍSTICAS TÉCNICAS / TECHNICAL DETAILS

Composición / <i>Composition</i>		100% PL
Ancho / <i>Width</i>		140 cm. ±2%
Peso / <i>Weight</i>		350 gr/m² ±5%
Solidez del color a la luz <i>Colour fastness to light</i>	XENO ISO 105 B 12	4
Solidez del color al frote <i>Colour fastness to rubbing</i>	CROCK METER ISO 105 X 12	4/5 SECO - DRY 3/4 HÚMEDO - WET
Resistencia al deslizamiento de los hilos <i>Seam slippage</i>	ISO 13936-2	1,5 mm
Resistencia al pilling <i>Pilling resistance</i>	ISO 12945-2	4/5
Resistencia a la abrasión <i>Abrasion resistance</i>	MARTINDALE ISO 12947-2	> 40.000 CICLOS / RUBS
Características / <i>Characteristics</i>	REPELENTE AL AGUA Y AL ACEITE - ANTIESTÁTICO - NO ENCOGE / WATER REPELLENT - OIL REPELLENT - ANTISTATIC - NO-SHRINK	

Símbolos de cuidado y limpieza / *Care label*



KALAHARI & CASABLANCA

Comportamiento frente al fuego / <i>Fire retardant</i>	ITALIA / <i>ITALY</i>	UNI 9175 Class 1IM
	EUROPA / <i>EUROPE</i>	EN 1021-1:2006 EN 1021-2:2006
	INGLATERRA / <i>ENGLAND</i>	BS 5852-0:1979 (cigarette) BS 5852-1:1979 (match) BS 5852 IS CRIB 5
	ALEMANIA / <i>GERMANY</i>	DIN 4102-1 Class B1
	EE.UU. / <i>U.S.A.</i>	California TB 117:2013
	NAUTICA / <i>NAUTICAL</i>	IMO res. MSC - 307 (88)

Estos valores se dan únicamente para información de buena fe y no pueden considerarse en ningún caso vinculantes. No se responde del uso inapropiado. **Se permiten ligeras diferencias de color entre diferentes lotes.** *The overmentioned data correspond to average values communicated in good faith, but they cannot be considered as a contract document. The company is not responsible for any inappropriate use of the product. Slight colour differences among several lots are admitted.*

www.mfarrugia.com

info@mfarrugia.com

+34 968 75 10 39 FAX +34 968 79 26 72