

# MARIANO FARRUGIA

## TESSUTI

### MÓNACO



#### CARACTERÍSTICAS TÉCNICAS / TECHNICAL DETAILS

Composición / <i>Composition</i>	<b>88% PVC - 7% PL - 4% CO 1% PU (polycarbonate)</b>	
Ancho / <i>Width</i>	<b>140 cm.</b>	
Peso / <i>Weight</i>	<b>715 ±10% gr/m<sup>2</sup></b>	
Espesor / <i>Thickness</i>	<b>1,1 mm ±0,2</b>	
Resistencia a la tracción <i>Tensile resistance</i>	UNI EN ISO 1421	≥ <b>25 daN/5cm</b> LARGO - <i>LENGTH</i> ≥ <b>15 daN/5cm</b> ANCHO - <i>WIDTH</i>
Resistencia a la rotura <i>Extension at break</i>	UNI EN ISO 1421	≥ <b>23%</b> LARGO - <i>LENGTH</i> ≥ <b>140%</b> ANCHO - <i>WIDTH</i>
Resistencia al desgarro <i>Tear strength</i>	UNI 4818 P9	≥ <b>9 daN</b> LARGO <i>LENGTH</i> ≥ <b>7 daN</b> ANCHO - <i>WIDTH</i>
Adherencia del recubrimiento / <i>Coating adhesion</i>	UNI EN ISO 2411	≥ <b>3 daN/5 cm</b>
Solidez del color al frote - ESCALA DE GRISES <i>Colour fastness to rubbing - GREY SCALE</i>	CROCK METER ISO 105 X 12	≥ <b>5 SECO - DRY</b> ≥ <b>5 HÚMEDO - WET</b>
Solidez del color a la luz artificial - ESCALA DE AZULES <i>Colour fastness to artificial light - BLUE SCALE</i>	XENO ISO 105 B 02	≥ <b>7</b>
Resistencia a la flexión tras 4 semanas de jungle test <i>Flexing endurance after 4 weeks jungle test</i>	BALLY UNI 4818 92-13 GARANTIA 7 AÑOS 7 YEARS GUARANTEE	≥ <b>200.000</b> CICLOS - <i>RUBS</i>
Resistencia a la abrasión <i>Abrasion resistance</i>	MARTINDALE ISO 5470-2	≥ <b>200.000</b> CICLOS - <i>RUBS</i>
Solidez del color al alcohol / <i>Colour fastness to alcohol</i>	VESLIC	≥ <b>100</b> CICLOS - <i>RUBS</i>
Antimicrobiano - Antimicótico <i>Antimicrobial - Antimycotic</i>	<b>FRESCO - HIGIÉNICO Y SIN OLORES</b> <i>FRESH - HYGIENIC - ODOR FREE</i>	
Características <i>Characteristics</i>	<b>EXENTO DE FTALATOS - ELÁSTICO - SUAVE</b> <i>PHTHALATE FREE - STRETCHY - SOFT</i>	
(SOLO BAJO PEDIDO) - Si se microperfora / (ONLY ON REQUEST) - If micro-perforated <b>TRANSPIRABLE /BREATHABLE</b>		
Símbolos de cuidado y limpieza <i>Care label</i>		
Atención <i>Warning</i>	RECOMENDAMOS EL USO DE PEGAMENTOS POLIURETÁNICOS <i>WE RECOMMEND THE USE OF POLYURETHANE GLUES</i>	
Comportamiento frente al fuego <i>Fire retardant</i>	ITALIA / <i>ITALY</i> EUROPA / <i>EUROPE</i> INGLATERRA / <i>ENGLAND</i>  EE.UU. / <i>U.S.A.</i> NAUTICA / <i>NAUTICAL</i>	UNI 9175 Class 1IM EN 1021:2014 part 1 - 2 BS 5852:1979 IS 0 (cigarette) BS 5852:1979 IS 1 (match) California TB 117:2013 FTP Code 307(88):10 Annex 1 Part 8
Sólo bajo pedido (min 300 mtl en 4 semanas) <i>Only on request (min 300 mtl in 4 weeks)</i>	FRANCIA / <i>FRANCE</i> ALEMANIA / <i>GERMANY</i> INGLATERRA / <i>ENGLAND</i>	NF-P 503 Class M1 (MANO DIFERENTE) DIN 4102-1 Class B1 BS 5852 IS 11 (crib 5)

Estos valores se dan únicamente para información de buena fe y no pueden considerarse en ningún caso vinculantes. No se responde del uso inapropiado. **Se permiten ligeras diferencias de color entre diferentes lotes.** *The overmentioned data correspond to average values communicated in good faith, but they cannot be considered as a contract document. The company is not responsible for any inappropriate use of the product. Slight colour differences among several lots are admitted.*

[www.mfarrugia.com](http://www.mfarrugia.com)

[info@mfarrugia.com](mailto:info@mfarrugia.com)

+34 968 75 10 39 FAX +34 968 79 26 72