

MARIANO FARRUGIA

T E S S U T I

SAINT TROPEZ



CARACTERÍSTICAS TÉCNICAS / TECHNICAL DETAILS

| | | |
|--|--|---|
| Código aduanero / Customs code | | 59031090 |
| Código alfanumérico artículo / Alphanumeric article code | | 02357 001 |
| Composición / Composition | | 68% PVC - 32% CO |
| Ancho / Width | UNI EN 1773 | 140 cm. |
| Peso / Weight | UNI 5114 | 680 gr/m² ±5% |
| Espesor / Thickness | | 1,25 mm ±0,1 |
| Longitud pieza / Roll length | | ±30 mt |
| Solidez del color al frote (seco - húmedo) Colour fastness to rubbing (dry - wet) | ISO 105 X 12 | 4/5 SECO - DRY 4-5 HÚMEDO - WET |
| Solidez del color a la luz artificial Colour fastness to artificial light | ISO 105 B 02 | ≥ 5 XENO |
| Resistencia a la tracción (trama - urdimbre) Tensile resistance (warp - weft) | ISO 1421 | ≥ 350 N URDIMBRE - WARP ≥ 300 N TRAMA - WEFT |
| Resistencia a la rotura (trama - urdimbre) Extension at break (warp - Weft) | ISO 1421 | ≥ 5% URDIMBRE - WARP ≥ 15% TRAMA - WEFT |
| Resistencia al desgarrar (trama - urdimbre) Tear strength (warp - weft) | ISO 4818 - P9 | ≥ 40 N URDIMBRE - WARP ≥ 40 N TRAMA - WEFT |
| Adherencia del recubrimiento (trama - urdimbre) Coating adhesion (warp - weft) | ISO 2411 | ≥ 30 N5cm URDIMBRE - WARP ≥ 30 N5cm TRAMA - WEFT |
| Flexión ciclos / Flexion cycles | ISO 4818 - P13 | > 150.000 BALLY |
| Resistencia a la abrasión / Abrasion resistance | ISO 5470-2 | > 150.000 MARTINDALE |
| Resistencia a la temperatura Temperature resistance | -30°/+70° DIN 53361 | OK |
| Resistencia bacteriana y fúngica Bacterial and fungal resistance | JIS Z 2801 - ISO 846 A | Sanitized® |
| Libre de ftalato / Phthalate free | | |
| Comportamiento frente al fuego Fire retardant | UNI 9175 1IM / EN 1021 part 1-2 / BS 5852:79 IS 0-1 BS 5852:06 IS 11 (Crib5) / NF-P 92 503 (M2) California TB:117 2013 / FTP Code 307 Part 8 | |
| Símbolos de cuidado y limpieza Care label | UNI EN ISO 3758 | |

Estos valores se dan únicamente para información de buena fe y no pueden considerarse en ningún caso vinculantes. No se responde del uso inapropiado. **Se permiten ligeras diferencias de color entre diferentes lotes.** The overmentioned data correspond to average values communicated in good faith, but they cannot be considered as a contract document. The company is not responsible for any inappropriate use of the product. **Slight colour differences among several lots are admitted.**

www.mfarrugia.com

info@mfarrugia.com

+34 968 75 10 39 FAX +34 968 79 26 72

Polígono Industrial La Herrada C/ Príncipe de Asturias 41 Apartado 452 30510 Yecla Murcia Spain