

# MARIANO FARRUGIA

## T E S S U T I

### SAN MARINO DIS. LISO



#### CARACTERÍSTICAS TÉCNICAS / TECHNICAL DETAILS

Código aduanero / <i>Customs code</i>		<b>58013700</b>
Código alfanumérico artículo / <i>Alphanumeric article code</i>		<b>09013 001</b>
Composición / <i>Composition</i>		<b>56% VI - 22% CO - 16% PL 6% Resin/Backing</b>
Ancho / <i>Width</i>	UNI EN 1773	<b>140 cm.</b>
Peso / <i>Weight</i>	UNI 5114	<b>490 gr/m<sup>2</sup> ±5% (± 30 gr/m<sup>2</sup> resina)</b>
Longitud pieza / <i>Roll length</i>		<b>±25 mt</b>
Resistencia a la tracción <i>Tensile resistance</i>	ISO 13934-1	<b>740 N</b> URDIMBRE - WARP <b>730 N</b> TRAMA - WEFT
Resistencia al desgarre <i>Tear strength</i>	ISO 13937-3	<b>33 N</b> URDIMBRE - WARP <b>47 N</b> TRAMA - WEFT
Resistencia al deslizamiento de la costura <i>Seam slippage</i>	BS 3320	<b>&gt; 200</b> URDIMBRE - WARP <b>&gt; 200</b> TRAMA - WEFT
Solidez del color al frote <i>Colour fastness to rubbing</i>	ISO 105 X 12	<b>5</b> SECO - DRY <b>4/5</b> HÚMEDO - WET
Solidez del color a la luz artificial <i>Colour fastness to artificial light</i>	ISO 105 B 02	<b>4-5</b> XENO
Resistencia al pilling <i>Pilling resistance</i>	ISO 5470-2	<b>5</b>
Resistencia a la abrasión <i>Abrasion resistance</i>	ISO 12947-2	<b>&gt; 85.000</b> MARTINDALE
Comportamiento frente al fuego / <i>Fire retardant</i>	ITALIA / ITALY EUROPA / EUROPE INGLATERRA / ENGLAND EE.UU. / U.S.A. NAUTICA / NAUTICAL	UNI 9175 Classe 11M EN 1021 part 1-2 BS 5852:79 IS 0-1 California TB:117 2013 FTP Code 307 Part 8
Símbolos de cuidado y limpieza / <i>Care label</i>	UNI EN ISO 3758	

Estos valores se dan únicamente para información de buena fe y no pueden considerarse en ningún caso vinculantes. No se responde del uso inapropiado. **Se permiten ligeras diferencias de color entre diferentes lotes.** *The overmentioned data correspond to average values communicated in good faith, but they cannot be considered as a contract document. The company is not responsible for any inappropriate use of the product. Slight colour differences among several lots are admitted.*

[www.mfarrugia.com](http://www.mfarrugia.com)

[info@mfarrugia.com](mailto:info@mfarrugia.com)

+34 968 75 10 39 FAX +34 968 79 26 72