

MARIANO FARRUGIA

TESSUTI



KENIA TEXTURA

CARACTERÍSTICAS TÉCNICAS / TECHNICAL DETAILS

Composición / <i>Composition</i>		84% PVC - 16% CO
Ancho / <i>Width</i>		137 cm.
Peso / <i>Weight</i>		750 gr/m² ±5%
Espesor / <i>Thickness</i>		1,3 mm ±0,2 mm
Resistencia a la tracción <i>Tensile resistance</i>	DIN EN ISO 1421	> 24 daN/5cm LARGO - <i>LENGTH</i> > 15 daN/5cm ANCHO - <i>WIDTH</i>
Resistencia a la rotura <i>Extension at break</i>	DIN EN ISO 4674 - 1B	> 13% LARGO - <i>LENGTH</i> > 10% ANCHO - <i>WIDTH</i>
Solidez del color al frote <i>Colour fastness to rubbing</i>	CROCK METER DIN EN ISO 105 X 12	4/5 SECO - <i>DRY</i> 4/5 HÚMEDO - <i>WET</i>
Solidez del color a la luz artificial <i>Colour fastness to artificial light</i>	XENO DIN EN ISO 105 X 12	4/5 SECO - <i>DRY</i> 4/5 HÚMEDO - <i>WET</i>
Resistencia a la abrasión <i>Abrasion resistance</i>	MARTINDALE DIN EN ISO 5470-2	> 40.000 CICLOS - <i>RUBS</i>
Exento de <i>Free from</i>	COL / AZO / CD / FCKW / PCB / PCP / PCT FORMALDEIDE / FORMALDEHYDE	
Símbolos de cuidado y limpieza / <i>Care label</i>		
Comportamiento frente al fuego / <i>Fire retardant</i>	ITALIA / <i>ITALY</i> EUROPA / <i>EUROPE</i> INGLATERRA / <i>ENGLAND</i> ALEMANIA / <i>GERMANY</i> FRANCIA / <i>FRANCE</i> EE.UU. / <i>U.S.A.</i> NAUTICA / <i>NAUTICAL</i>	UNI 9175 Class 1IM EN 1021-1:2006 / EN 1021-2:2006 BS 5852 IS CRIB 5 BS 5852 IS CRIB 5 NF-P 503 Class M1 California TB 117 2013 FTP Code 307(88): 10 Annex 1 Part 8

Algunos tintes utilizados en la ropa (ej. vaqueros) pueden migrar en colores claros de este artículo. Este fenómeno aumenta con la humedad y temperatura. No se asume ninguna responsabilidad por la transferencia de color. *Some dyes for clothing and accessories (ex. jeans) may migrate to the bright colour of this article. This phenomenon increases with the humidity and the temperature. No responsibility is assumed for the colour transfer.*

Estos valores se dan únicamente para información de buena fe y no pueden considerarse en ningún caso vinculantes. No se responde del uso inapropiado. **Se permiten ligeras diferencias de color entre diferentes lotes.** *The overmentioned data correspond to average values communicated in good faith, but they cannot be considered as a contract document. The company is not responsible for any inappropriate use of the product. Slight colour differences among several lots are admitted.*

www.mfarrugia.com

info@mfarrugia.com

+34 968 75 10 39 FAX +34 968 79 26 72